



# 金东纸业(江苏)股份有限公司

## GOLD EAST PAPER (JIANGSU) CO., LTD.

中国 江苏省 镇江市 大港 兴港东路8号 邮编 212132  
 8 Xinggang Dong Rd., Dagang, Zhenjiang 212132, Jiangsu. PR China  
 Telephone : +86- 511- 88998888 Fax : +86- 511- 88997000 Web: www. goldeastpaper. com

### Specifications

**C2S Art Paper /Matt(Nevia)**

**Jul. 2015 N Edition**

Item	Unit	Test Method Reference	80 g/m <sup>2</sup>	85 g/m <sup>2</sup>	90 g/m <sup>2</sup>	95 g/m <sup>2</sup>	100 g/m <sup>2</sup>	105 g/m <sup>2</sup>	115 g/m <sup>2</sup>	120 g/m <sup>2</sup>	128 g/m <sup>2</sup>	130 g/m <sup>2</sup>	135g/m <sup>2</sup>	140 g/m <sup>2</sup>	150 g/m <sup>2</sup>	157 g/m <sup>2</sup>	160g/m <sup>2</sup>	170 g/m <sup>2</sup>	180 g/m <sup>2</sup>	200 g/m <sup>2</sup>
Basis Weight	g/m <sup>2</sup>	ISO 536	80±3	85±3	90±3	95±3	100±4	105±4	115±4	120±4	128±4	130±4	135±4	140±4	150±4	157±4	160±4	170±5	180±5	200±5
Thickness	μ m	ISO 534	72±4	75±4	78±4	83±4	91±4	95±4	106±4	111±4	118±4	120±4	129±4	134±4	144±4	150±4	153±4	161±5	177±5	200±5
Brightness	%	ISO 2470/1	89-92	89-92	89-92	89-92	89-92	89-92	89-92	89-92	89-92	89-92	89-92	89-92	89-92	89-92	89-92	89-92	89-92	89-92
Opacity	%	ISO 2471	88-91	89-92	89-92	90-93	93-96	93-96	94-97	94-97	95-98	95-98	96-99	96-99	96-99	97-100	97-100	97-100	97-100	98-100
Roughness	μ m	ISO 8791/4	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7
Gloss	%	T 480	32±5	32±5	32±5	32±5	32±5	30±5	30±5	30±5	30±5	30±5	30±5	30±5	30±5	30±5	30±5	30±5	30±5	30±5

GOLD EAST PAPER (JIANGSU) CO.,LTD.

