



宁波亚洲浆纸业有限公司
NINGBO ASIA PULP & PAPER CO.,LTD



CHIEFTAIN

C2S GLOSS COVER

Basis Weight		Thickness		Stiffness (Taber 15°)	
g/m ² ±3%	24"x36" 500 (lb)	µm (±15)	pt (±0.6)	mN·m	
				CD≥	MD≥
250	154	250	9.8	2.2	4.4
280	172	285	11.2	3.5	7.0
300	184	305	12.0	4.2	8.0
350	215	360	14.2	6.5	12.0
400	246	415	16.3	9.0	17.0

Property	Unit	Value
PPS (Top/Back)	µm	Top: < 350gsm 1.4; ≥350gsm 1.5 Back: < 300gsm 1.4; ≥350gsm 1.6
Moisture	%	6.5±1.0
Brightness (Top/Back)	%	92.0±2.0
75°Gloss (Top/Back)	%	≥60
IGT Blister (Top/Back)	m/s	≥1.5
COBB Test (60s) (Top/Back)	g/m ²	40±15
PLY bonding	J/m ²	≥150
Squareness	mm	≤2.0
Size Deviation	mm	≤2.0

Test condition (ISO): temp (23±1)^oC, relative humidity (50±2)%

Note: Shaded substances are non-regular substances which are not produced regularly.