

TECHNICAL DATA

OFFWHITE / 70 gsm / 1.80

Parameter	Value	Tolerance	Comment
Basis Weight	70 g/m ²	+/- 4 g/m ²	As specified by Customer
Bulk / Volume	1.8		As specified by Customer
Caliper	126 micron	+/- 3 micron	180 micron maximum
Brightness	75 iso	+/- 0.75	
Shade	9 (Cream)	+/- 0.5	As specified by customer
Opacity	89	+/- 1	Dependant on grammage/caliper
Moisture	8%	+/- 0.5	
Tear		+/- 0.4	
Tensile		+/- 0.4	
Main furnish	85 to 90% mechanical groundwood		Produced from Norwegian Spruce
Secondary furnish	10 to 15% Cellulose (Spruce)		Purchased from Rottneros, Sweden
Wrapping	Kraft wrappers		2 layers
Cores	76mm strawboard		152mm cores on request
Joins	Maximum 2 joins per reel		Marked by red line on reel
Reel Diameter	1000mm or 1150mm		As specified by customer
Accreditation	FSC	Mix Credit NC-COC-016937	FSC Paper on request

All paper supplied according to the General Trade Rules for the supply of paper and paperboard

Should Technical Data be required for a specific grammage / caliper combination, this can be provided upon request