



晨鸣集团
CHENMING GROUP

Uncoated Woodfree Paper-Creamy

云豹 米黄簿本纸

ZJCM

TECHNICAL SPECIFICATIONS

Items	项目	Unit	Standard/ Method	Parameters												
Basis Weight	定量	gsm	ISO 536	65	68	75	78	95	98							
Caliper	厚度	µm	ISO 534	83	87	96	100	122	125							
ISO Brightness	亮度	%	ISO 2470-1	74	74	74	74	74	74							
Smoothness	平滑度	s	ISO 5627	≥30	≥30	≥30	≥30	≥30	≥30							
Moisture	水分	%	ISO 287	5.5-6.0	5.5-6.0	5.5-6.0	5.5-6.0	5.5-6.0	5.5-6.0							
COBB	表面吸收重量	gsm	ISO 535	30-40	30-40	30-40	30-40	30-40	30-40							
Surface Printing Intensity	表面印刷强度	m/s	JGT	≥1.6	≥1.6	≥1.6	≥1.6	≥1.6	≥1.6							

* Test conditions: ISO Temperature: 23±1°C ; Humidity: 50±2%RH; Humidity: 50±2%RH; Humidity: 50±2%RH

The Bulk of 1.28, 1.33, 1.40 and 1.53 are available